

REPORT NO TC SL 21033/DS/12
REPORT ON DRYING SHRINKAGE TEST ON AGGREGATES

Client Cullimore's Mix Ltd.
Netherhills
Whitminster
Gloucestershire
GL2 7PD

Source of Material Ashton Keynes

Material Description 4/20mm Aggregate

Date Received 30th January 2012

Requirements Determination of drying shrinkage.

Date Test Started 20th February 2012


Test Method BS EN 1367-4 : 2008

Results

Drying Shrinkage = 0.025 %

95 % confidence limits = 0.0039 %

SIGNED:



Bob Potter

Date of Issue:- 29th March 2012